

Technical Data Sheet



Vision R Smart Black Back Stretch

Material	100% Polyester			
Stock widths	app. 320 cm / 5.05m			
Weight acc. to DIN EN 12127	260.00	[g/m ²]	+- 5	[%]

Shrinkage

Heat Shrinkage, 195 degrees, 90sec, lengthwise acc. to PAO_13	-2.50	[%]	+- 1	[%]
Heat Shrinkage, 195 degrees, 90sec, Crosswise acc. to PAO_13	-1.00	[%]	+- 1	[%]

Tearing strength

Elongation at 100 N, longitudinal direction acc. to DIN EN ISO 13934-1	13.00	[%]	+- 20	[%]
Elongation at 100 N, cross direction acc. to DIN EN ISO 13934-1	9.00	[%]	+- 20	[%]
Maximum tensile elongation, longitudinal direction acc. to DIN EN ISO 13934-1	29.00	[%]	+- 20	[%]
Maximum tensile elongation, cross direction acc. to DIN EN ISO 13934-1	15.00	[%]	+- 20	[%]
Maximum tearing strength, longitudinal direction acc. to DIN EN ISO 13934-1	min. 230.00	[N/5 cm]		
Maximum tearing strength, cross direction acc. to DIN EN ISO 13934-1	min. 700.00	[N/5 cm]		

Fire Retardancy: B1 / EN13501



Roseash Limited, Unit B The Height Business Centre, Ibstone Road, Stokenchurch, Buckinghamshire, HP14 3BG
T: 01494 760240 E : sales@dpm.com W : www.dpm.com